

2 7850 TARAX

ARTIKEL ITEM	080	100	130	160	200	240
MANTELMATERIAL MATERIAL SLEEVE	POLYESTER					
KERNMATERIAL MATERIAL CORE	HMPE					
TECHNOLOGIE TECHNOLOGY						

NENNDURCHMESSER NOMINAL DIAMETER	1,0 mm ± 0,1 mm	1,1 mm ± 0,1 mm	1,3 mm ± 0,15 mm	1,5 mm ± 0,15 mm	1,7 mm ± 0,15 mm	1,9 mm ± 0,15 mm
NENNGEWICHT NOMINAL WEIGHT PER METER	0,70 g/m ± 0,10 g/m	1,00 g/m ± 0,10 g/m	1,30 g/m ± 0,15 g/m	1,70 g/m ± 0,15 g/m	2,0 g/m ± 0,15 g/m	2,3 g/m ± 0,15 g/m
HÖCHSTZUGKRAFT MIN. Ø BREAKING STRENGTH MIN Ø	≥ 80 daN	≥ 100 daN	≥ 130 daN	≥ 160 daN	≥ 200 daN	≥ 240 daN
DEHNUNG BEI HÖCHSTZUGKRAFT MIN. ELONGATION AT MIN.BREAKING	≤ 5,0 %	≤ 5,0 %	≤ 5,0 %	≤ 5,0 %	≤ 5,0 %	≤ 5,0 %
HÖCHSTZUGKRAFT GEMITTELT* AVERAGE BREAKING STRENGTH*	Ø 100 daN	Ø 125 daN	Ø 165 daN	Ø 205 daN	Ø 255 daN	Ø 295 daN

* Average value of all productions; helps to make an estimate of the real values that can be achieved. Only the nominal value marked as "Höchstzugkraft min. Ø | Breaking strength min Ø" can be guaranteed! *
Technische Änderungen vorbehalten | Subject to change technical data without notice

Das bewährte Standard-Modell unter den ummantelten Dyneema-Leinen. Ausgestattet mit einem innen liegenden Dyneema®-Geflecht bietet die Leine ein hohes Maß an Festigkeit und Formstabilität. Ohne Verstreckung des Kern-Materials und mit einer robusten Polyester- Ummantelung erfüllt dieses Modell alle grundlegenden Anforderungen, die man von einem soliden und langlebigen Modell erwarten darf. Fein differenzierte Abstufungen in den Festigkeiten und eine große Bandbreite an Farbdesigns innerhalb dieser Modellreihe eröffnen Raum für flexible Anwendungsmöglichkeiten.

Our tried-and-tested standard Dyneema line. It has a Dyneema® braided core that provides a high degree of strength and stability. The core will not stretch, while the robust polyester sheath ensures that this line does everything required of a high-strength and durable line. The wide range of strengths, colours and patterns makes the TARAX line suitable for a wide variety of applications.

2 7850 TARAX

- Dyneema® Kerngeflecht für eine hohe Festigkeit und Formstabilität mit einem robusten PES-Mantel
- hohe Knotenfestigkeit
- sehr gutes Handling durch Thermo Shield Verfahren
- Arbeitsdehnung maximal 0,8 %

Farben und MOQ siehe aktuelle Preisliste

- *high-tensile and stable Dyneema® core with a robust PES sheath*
- *good knotting characteristics*
- *Thermo Shield treatment for perfect handling*
- *maximal elongation 0,8 %*

Colors and MOQ please refer actual pricelist



THERMO SHIELD describes a thermal treatment that anticipates the shrinkage of the yarns equal and durable. The process perfectly aligns the core and sheath yarns, make the line dimensionally stable and leads to the known suppleness.