





2 7235

ABRAX



ARTIKEL ITEM CODE	380	650
MANTELMATERIAL MATERIAL SLEEVE MATÉRIAL GAINE	POLYESTER	
KERNMATERIAL MATERIAL CORE MATÉRIAL AME		
SPEZIFIKATION CHARACTERISTIC		  

NENNDURCHMESSER NOMINAL DIAMETER DIAMÈTRE NOMINAL	2,6 x 3,4 mm ± 0,3 mm	3,8 x 4,3 mm ± 0,3 mm
NENNGEWICHT NOMINAL WEIGHT PER METER POIDS MÉTRIQUE NOMINAL	7,10 g/m ± 0,50 g/m	13,50 g/m ± 0,50 g/m
HÖCHSTZUGKRAFT MIN. Ø BREAKING STRENGTH MIN Ø CHARGE DE RUPTURE MIN Ø	≥ 380 daN	≥ 650 daN
DEHNUNG BEI HZK MIN. ELONGATION AT MIN.BREAKING ALLONGEMENT À LA CHARGE DE RUPTURE MIN.	≤ 14,0 %	≤ 15,0 %
NENNDEHNUNG BEI (EINZELLOSE)	> 0,4 %	> 0,4 %
NOMINAL ELONGATION AT (SINGLE LOT)	> 0,5 %	> 0,5 %
ALLONGEMENT NOMINAL À (LOT INDIVIDUEL)	> 1,0 %	> 0,8 %
5 daN	> 1,0 %	> 1,0 %
10 daN	> 1,0 %	> 1,0 %
15 daN	> 2,0 %	> 2,0 %
20 daN	> 3,5 %	> 2,5 %
25 daN	> 7,0 %	> 3,5 %
50 daN		
100 daN		
200 daN		

Technische Änderungen vorbehalten | Subject to change technical data without notice | Sauf changements techniques





2 7235 ABRAX

- ausgerüstetes Polyester Geflecht
- sehr gutes Handling durch Thermo Shield Verfahren
- hohe Reibungsresistenz
- sehr gut spleißbar

Farben und MOQ siehe aktuelle Preisliste

- *coated polyester braiding*
- *Thermo Shield treatment for perfect handling*
- *high friction resistance*
- *good spliceability*

Colors and MOQ please refer actual pricelist

	<p>Used by EDELRID for 20 years, this is a thermal finishing process which evenly and permanently stabilizes yarns against shrinkage. The individual yarns thereby form an even, stable unit giving the line its characteristic suppleness.</p>
	<p>The finishing protects the textile fibers of the line, thus increasing the lifetime and handling of the line. Abrasion resistance and stiffness can be specifically adjusted. Where necessary, the finish is supplemented with components for UV protection.</p>
	<p>The SPLICEACT product attribute is the guarantee of a line with outstanding splicing properties, ensured by the balance between the yarns used in conjunction with the design parameters.</p>
	<p>The STRETCHACT process stretches the lines in an optimally-adjusted ratio, anticipating the natural properties of the material to guarantee products with outstanding stretch and recovery properties. Our claim, your satisfaction: the minimum possible stretch with outstanding recovery characteristics.</p>